

Schott N-LAK34 Glass

Category : Ceramic , Glass

Material Notes:

Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-N-LAK34-Glass.php

Physical Properties	Metric	English	Comments
Density	4.02 g/cc	0.145 lb/in ³	

Mechanical Properties	Metric	English	Comments
Knoop Microhardness	740	740	.1/20
Modulus of Elasticity	117 GPa	17000 ksi	
Poissons Ratio	0.29	0.29	
Shear Modulus	45.0 GPa	6530 ksi	calculated

Thermal Properties	Metric	English	Comments
CTE, linear	5.80 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	3.22 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature -30.0 - 70.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 158 $\text{Å}^\circ\text{F}$	
	6.90 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	3.83 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 20.0 - 300 $\text{Å}^\circ\text{C}$	@Temperature 68.0 - 572 $\text{Å}^\circ\text{F}$	
Specific Heat Capacity	0.520 J/g- $\text{Å}^\circ\text{C}$	0.124 BTU/lb- $\text{Å}^\circ\text{F}$	
Thermal Conductivity	0.820 W/m-K	5.69 BTU-in/hr-ft Å^2 - $\text{Å}^\circ\text{F}$	
Transformation Temperature, Tg	668 $\text{Å}^\circ\text{C}$	1230 $\text{Å}^\circ\text{F}$	

Optical Properties	Metric	English	Comments
Refractive Index	1.72916	1.72916	n _d
	@Wavelength 587.6 nm	@Wavelength 587.6 nm	
	1.73235	1.73235	n _e
	@Wavelength 546.1 nm	@Wavelength 546.1 nm	
	96.3 %	96.3 %	

Transmission Visible Optical Properties	Metric @Thickness 10.0 mm, Wavelength 380 nm	English @Thickness 0.394 in, Wavelength 380 nm	Comments
	98.3 %	98.3 %	
	@Thickness 10.0 mm, Wavelength 405 nm	@Thickness 0.394 in, Wavelength 405 nm	
	99.5 %	99.5 %	
	@Thickness 10.0 mm, Wavelength 460 nm	@Thickness 0.394 in, Wavelength 460 nm	
	99.8 %	99.8 %	
	@Thickness 10.0 mm, Wavelength 580 nm	@Thickness 0.394 in, Wavelength 580 nm	
	99.9 %	99.9 %	
	@Thickness 10.0 mm, Wavelength 700 nm	@Thickness 0.394 in, Wavelength 700 nm	
IR Transmittance	39.8 %	39.8 %	
	@Thickness 10.0 mm, Wavelength 2500 nm	@Thickness 0.394 in, Wavelength 2500 nm	
	98.4 %	98.4 %	
	@Thickness 10.0 mm, Wavelength 1530 nm	@Thickness 0.394 in, Wavelength 1530 nm	
UV Transmittance	1.4 %	1.4 %	
	@Thickness 10.0 mm, Wavelength 270 nm	@Thickness 0.394 in, Wavelength 270 nm	
	28.1 %	28.1 %	
	@Thickness 10.0 mm, Wavelength 300 nm	@Thickness 0.394 in, Wavelength 300 nm	
	71.3 %	71.3 %	
	@Thickness 10.0 mm, Wavelength 334 nm	@Thickness 0.394 in, Wavelength 334 nm	
	94.1 %	94.1 %	
	@Thickness 10.0 mm, Wavelength 370 nm	@Thickness 0.394 in, Wavelength 370 nm	

Chemical Properties	Metric	English	Comments
Acid Class, SR	52.3	52.3	
Alkali Class, AR	1.0	1.0	
Stain Resistance Class, FR	0.00	0.00	

Descriptive Properties	Value	Comments
B	0	
Climatic Resistance Test CR	1	
HG	2	
K (10-6mm ² /N)	1.52	
Phosphate Resistance PR	3.3	
T1013.0 (Å°C)	668	
T107.6 (Å°C)	740	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China