

Schott RG1000 Long Pass Filter

Category : Ceramic , Glass , Optical , Filter

Material Notes:

Ionically colored glass. Data provided by the manufacturer, Schott Glas Mainz. Similar glasses include GG395, GG400, GG420, GG435, GG455, GG475, GG495, OG515, OG530, OG550, OG570, OG590, RG610, RG630, RG645, RG665, RG695, RG715, RG780, RG830, RG850, GG385, WG225, WG280, WG295, WG305, WG320

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-RG1000-Long-Pass-Filter.php

Physical Properties	Metric	English	Comments
Density	2.75 g/cc	0.0994 lb/in ³	

Thermal Properties	Metric	English	Comments
CTE, linear	9.50 Åµm/m-Å°C	5.28 Åµin/in-Å°F	
	@Temperature -30.0 - 70.0 Å°C	@Temperature -22.0 - 158 Å°F	
	10.5 Åµm/m-Å°C	5.83 Åµin/in-Å°F	
	@Temperature 20.0 - 300 Å°C	@Temperature 68.0 - 572 Å°F	
Transformation Temperature, Tg	478 Å°C	892 Å°F	
Glass Temperature Coefficient	0.23	0.23	

Optical Properties	Metric	English	Comments
Refractive Index	1.55	1.55	He
	@Wavelength 587.6 nm	@Wavelength 587.6 nm	
	1.55	1.55	Hg
	@Wavelength 1014 nm	@Wavelength 1014 nm	
IR Transmittance	89 %	89 %	Internal transmittance of 98% from 1600-2000 nm.
	@Wavelength 1600 - 2000 nm	@Wavelength 1600 - 2000 nm	
UV Transmittance	<= 0.0010 %	<= 0.0010 %	Internal transmittance of 0.001% from 200-390 nm.
	@Wavelength 200 - 390 nm	@Wavelength 200 - 390 nm	
Reflection Coefficient, Visible (0-1)	0.91	0.91	

Chemical Properties	Metric	English	Comments
Acid Class, SR	53.4	53.4	
Alkali Class, AR	1	1	
Stain Resistance Class, FR	3	3	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China