

## Schwartz Technical Plastics LAMIGAMIDÂ® 307 Cast Polyamide 6, Heat Stabilized, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Heat Stabilized

### Material Notes:

Application: slippers, inserts for coupling boxes  
Information provided by Schwartz Technical Plastics GmbH

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Schwartz-Technical-Plastics-LAMIGAMID-307-Cast-Polyamide-6-Heat-Stabilized-Conditioned.php](http://www.lookpolymers.com/polymer_Schwartz-Technical-Plastics-LAMIGAMID-307-Cast-Polyamide-6-Heat-Stabilized-Conditioned.php)

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in <sup>3</sup>	ISO R 1183
Moisture Absorption at Equilibrium	2.2 %	2.2 %	DIN 53473
Water Absorption at Saturation	<= 7.0 % @Temperature 20.0 Â°C	<= 7.0 % @Temperature 68.0 Â°F	ISO R 62

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	115 MPa	16700 psi	Hc 30; ISO 2039; partially
Tensile Strength, Yield	45.0 MPa	6530 psi	ISO-DIS 527
Creep Strength	>= 4.00 MPa	>= 580 psi	1% elongation, 1000 h; DIN 53444
	>= 8.00 MPa	>= 1160 psi	2% elongation, 1000 h; DIN 53444
Tensile Modulus	2.30 GPa	334 ksi	DIN 53457
Flexural Strength	40.0 MPa	5800 psi	DIN 54352
Flexural Modulus	2.00 GPa	290 ksi	DIN 53457
Compressive Strength	29.0 MPa	4210 psi	5% pressing; EN ISO 604
	46.0 MPa	6670 psi	10% pressing; EN ISO 604
	67.0 MPa	9720 psi	20% pressing; EN ISO 604
Izod Impact, Notched (ISO)	>= 15.0 kJ/m <sup>2</sup>	>= 7.14 ft-lb/in <sup>2</sup>	ISO 180-1A
Izod Impact Resistance	NB	NB	swinging hammer 0,1 DIN 51222; DIN 53453
Coefficient of Friction	0.040	0.040	With lubrication
Coefficient of Friction, Dynamic	0.31	0.31	no lube; Steel 2162, Rvst=2E-6m, p=0.05 Mpa, v=0.6 m/s, t=40Â°C
Tear Strength Test	>= 0.25	>= 0.25	ISO-DIS 527

Mechanical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear	70.0 - 80.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	38.9 - 44.4 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	DIN 53752
	@Temperature 20.0 - 100 $\text{Å}^\circ\text{C}$	@Temperature 68.0 - 212 $\text{Å}^\circ\text{F}$	
Specific Heat Capacity	1.67 J/g- $\text{Å}^\circ\text{C}$	0.399 BTU/lb- $\text{Å}^\circ\text{F}$	
Thermal Conductivity	0.250 W/m-K	1.74 BTU-in/hr-ft $\text{Å}^2$ - $\text{Å}^\circ\text{F}$	DIN 52612
Melting Point	215 $\text{Å}^\circ\text{C}$	419 $\text{Å}^\circ\text{F}$	ISO R 1218
Maximum Service Temperature, Air	120 $\text{Å}^\circ\text{C}$	248 $\text{Å}^\circ\text{F}$	Continuous
	180 $\text{Å}^\circ\text{C}$	356 $\text{Å}^\circ\text{F}$	Intermittent
Deflection Temperature at 0.46 MPa (66 psi)	200 $\text{Å}^\circ\text{C}$	392 $\text{Å}^\circ\text{F}$	V-notch; ISO R 75
Deflection Temperature at 1.8 MPa (264 psi)	110 $\text{Å}^\circ\text{C}$	230 $\text{Å}^\circ\text{F}$	V-notch; ISO R 75
Minimum Service Temperature, Air	-40.0 $\text{Å}^\circ\text{C}$	-40.0 $\text{Å}^\circ\text{F}$	Continuous

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	DIN 53482
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	DIN 53482
Dielectric Constant	3.7	3.7	DIN 53483
Dielectric Strength	20.0 kV/mm	508 kV/in	DIN 53481
Dielectric Loss Index	0.030	0.030	DIN 53483

Descriptive Properties	Value	Comments
Creepage/leakage Resistance	KA3b	DIN 53480

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China