

## Shakespeare Sanstat® CN125 .36mm Nylon 66 Monofilament

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 Fiber

### Material Notes:

Sanstat CN125 nylon 6,6 monofilaments have electrically conductive carbon suffused into the surface. The filaments have a carbon coating thickness of approximately 1 micron. Information provided by Shakespeare Company.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Shakespeare-Sanstat-CN12536mm-Nylon-66-Monofilament.php](http://www.lookpolymers.com/polymer_Shakespeare-Sanstat-CN12536mm-Nylon-66-Monofilament.php)

| Physical Properties | Metric                          | English  | Comments                    |
|---------------------|---------------------------------|--|-----------------------------|
| Density             | 1.33 g/cc<br>@Diameter 0.360 mm | 0.0480 lb/in <sup>3</sup><br>@Diameter 0.0142 in | Product yield of 7370 m/kg. |
| Fiber Count         | 1360 dtex                       | 1220 denier                                      | Per Filament                |

| Mechanical Properties | Metric      | English       | Comments           |
|-----------------------|-------------|---------------|--------------------|
| Elongation at Break   | 32 %        | 32 %          |                    |
| Tenacity              | 0.353 N/tex | 4.00 g/denier | 5 kg breaking load |

| Thermal Properties | Metric  | English  | Comments |
|--------------------|---|--|----------|
| Melting Point      | 254 Â°C   | 489 Â°F  |          |
| Shrinkage          | 5.00 %<br>@Temperature 175 Â°C,<br>Time 601 sec | 5.00 %<br>@Temperature 347 Â°F,<br>Time 0.167 hour |          |

| Electrical Properties  | Metric                             | English                            | Comments |
|------------------------|------------------------------------|------------------------------------|----------|
| Electrical Resistivity | 9000 ohm-cm<br><br><= 14000 ohm-cm | 9000 ohm-cm<br><br><= 14000 ohm-cm | Average  |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China