

Shamrock Technologies Fluoro FR- 150 Anti-dripping Thermoplastic Grade PTFE Additive

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic , Fluoropolymer , PTFE

Material Notes:

The addition of micronized polytetrafluoroethylene (PTFE) powder to polymeric resins (and to polymeric resins containing glass fiber) provides greatly increased resistance to surface wear and abrasion. PTFE has a very low coefficient of friction (0.04) and is therefore useful as an internal lubricant processing aid. Because the PTFE particles are inert, processing and the other physical properties of the thermoplastic resin are not adversely affected. As a result of the improved surface wear and slip, thermoplastic products containing FLUORO-TÂ® PTFE, look good longer while in use. The molecular weight and particle size distribution of the Shamrock series of FLUORO-T PTFE powders for thermoplastics are tailored to yield optimum improvements to wear resistance and surface friction, and flow easily during blending. Flame retardant Anti Dripping additive UL-94 Information provided by Shamrock Technologies

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shamrock-Technologies-Fluoro-FR-150-Anti-dripping-Thermoplastic-Grade-PTFE-Additive.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.15 g/cc	2.15 g/cc	Internal method
Bulk Density	0.350 - 0.550 g/cc	0.0126 - 0.0199 lb/inÂ³	ASTM D-4894
Additive Loading	5.0 - 25 %	5.0 - 25 %	

Mechanical Properties	Metric	English	Comments
Coefficient of Friction	0.040	0.040	

Thermal Properties	Metric	English	Comments
Melting Point	320 - 330 Â°C	608 - 626 Â°F	ASTM-D-4591

Descriptive Properties	Value	Comments
FDA Regulatory Information	21CFR;175.105;175.300;176.170;176.180	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China