

Shamrock Technologies Fluoro T^Â® 802 Thermoplastic Grade PTFE Additive

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic , Fluoropolymer , PTFE

Material Notes:

The addition of micronized polytetrafluoroethylene (PTFE) powder to polymeric resins provides greatly increased resistance to surface wear and abrasion. PTFE has a very low coefficient of friction (0.04) and is therefore useful as an internal lubricant processing aid. Because the PTFE particles are inert, processing and the other physical properties of the thermoplastic resin are not adversely affected. The optimum loading is typically 5 to 20 wt% PTFE. As a result of the improved surface wear and slip, thermoplastic products containing FLUORO-T^Â® PTFE, look good longer while in use. The molecular weight and particle size distribution of the Shamrock series of FLUORO-T PTFE powders for thermoplastics are tailored to yield optimum improvements to wear resistance and surface friction, and flow easily during blending. Low Friction Lubricant Wear Resistance Information provided by Shamrock Technologies.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shamrock-Technologies-Fluoro-T-802-Thermoplastic-Grade-PTFE-Additive.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.15 g/cc	2.15 g/cc	Internal method
Bulk Density	0.350 - 0.550 g/cc	0.0126 - 0.0199 lb/in ^{Â³}	ASTM D-4894
Additive Loading	5.0 - 25 %	5.0 - 25 %	When used as an additive
Particle Size	35 Âµm	35 Âµm	Mean Value, Laser diffraction; QSOP-5&75
	100 Âµm	100 Âµm	95%, Laser diffraction; QSOP-5&75

Mechanical Properties	Metric	English	Comments
Coefficient of Friction	0.040	0.040	

Thermal Properties	Metric	English	Comments
Melting Point	320 - 330 Â°C	608 - 626 Â°F	ASTM-D-4591

Descriptive Properties	Value	Comments
Appearance	Fine powder	
Color	White	
FDA Regulatory Information	21CFR;175.105;175.300;176.170;176.180	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China