

Shandong Dongyue Polymer DF-21B PTFE Presintered Resin

Category: Polymer, Thermoplastic, Fluoropolymer, PTFE

Material Notes:

Usage: The presintered resin is suitable for continuously extruding of all types, pushing and pressing PTFE rod, tube and special shape. Packing: PTFE is packed in double layer PVC bags inside and in hard circular barrels outside. Storage: PTFE should be stored in a clean, dry warehouse to protect from dust, moisture, etc. Transportation: The products are transported according to non-dangerous products. Heat, moisture, freezing and strong shock should be avoided during transportation. Over-bumpiness and compression is apt to make the resin bind together. Conformable with Q/DYG 007-2004Information provided by Shandong Dongyue Polymer Material Co., Ltd

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shandong-Dongyue-Polymer-DF-21B-PTFE-Presintered-Resin.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------------|------------------------|----------|
| Bulk Density | 0.500 - 0.800 g/cc | 0.0181 - 0.0289 lb/in³ | |
| Particle Size | <= 500 Âμm | <= 500 Âμm | |

| Thermal Properties | Metric | English | Comments |
|--------------------|--------------|--------------|----------|
| Melting Point | 322 - 332 °C | 612 - 630 °F | |

| Descriptive Properties | Value | Comments |
|-----------------------------|---|----------|
| Machining Method | Ram extrusion | |
| Powder Flow (g/min) | 450 | |
| Smoothness & Cleanliness | First Grade: Clean and white surface, no metal impurity, the impurity quantity from 1-3 mm doesn't exceed two | |
| | Qualified: Clean and white surface, no metal impurity, the impurity quantity from 1-3 mm doesn't exceed four | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China