

Shandong Dongyue Polymer DF-31A PTFE Pelletized Resin

Category: Polymer, Thermoplastic, Fluoropolymer, PTFE

Material Notes:

Usage: The resin is used to auto press molding and ram extrusion all kinds of rods, pipe etc.Packing: PTFE is packed in double layer PVC bags inside and in hard circular barrels outside. Storage: PTFE should be stored in a clean, dry warehouse to protect from dust, moisture, etc. Transportation: The products are transported according to non-dangerous products. Heat, moisture, freezing and strong shock should be avoided during transportation. Over-bumpiness and compression is apt to make the resin bind together. Conformable with Q/DYG 006-2004Information provided by Shandong Dongyue Polymer Material Co., Ltd

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shandong-Dongyue-Polymer-DF-31A-PTFE-Pelletized-Resin.php

Physical Properties	Metric	English	Comments
Density	0.700 - 0.900 g/cc	0.0253 - 0.0325 lb/in³	
Particle Size	500 - 700 Âμm	500 - 700 Âμm	

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 20.0 MPa	>= 2900 psi	
Elongation at Break	>= 200 %	>= 200 %	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.040 %	<= 0.040 %	

Descriptive Properties	Value	Comments
For Fabrication	Auto press molding and ram extrusion	
Powder Flow (g/min)	700	
Smoothness & Cleanliness	Grade 1: Test impurity quantity that equal or less than 1mm doesn't exceed two	
	Qualified: Test plate is white and homogeneous, no metal impurities, total impurity quantity <6	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China