

## Shandong Dongyue Shenzhou New Material Co DS2603 Fluoroelastomer Copolymer Gum

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Conformable with: Q/DYS 005-2007  
 Brief Introduction:FKM-DS2600 is copolymer of HFP and VDF. Normally it is white or light yellow translucent elastomer whose fluorine content is over 66%. After vulcanizing process, FKM products have excellent mechanical performance, outstanding anti oil property (fuel oil, synthesis oil, lubricating oil) and high thermal stability.  
 Main Applications:Widely used in high temperature, aviation, automobile, petroleum and chemical industries, oils, lubricants, etc. Mainly used to produce gaskets, O-rings, V-rings, sealing bowl with metal bone, diaphragms, tube, valve-plate, rolls, etc.  
 Properties: Middle and high viscosity, good milling and calendaring performance  
 Application: Calendaring sheet, skeletal oil seal, extruded hose etc.  
 Information Provided by Shandong Dongyue Shenzhou New Material Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Shandong-Dongyue-Shenzhou-New-Material-Co-DS2603-Fluoroelastomer-Copolymer-Gum.php](http://www.lookpolymers.com/polymer_Shandong-Dongyue-Shenzhou-New-Material-Co-DS2603-Fluoroelastomer-Copolymer-Gum.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.80 - 1.84 g/cc	1.80 - 1.84 g/cc	
Mooney Viscosity	61 - 79	61 - 79	ML(1+10); DS2603-1
	@Temperature 121 Â°C	@Temperature 250 Â°F	
	80 - 100	80 - 100	ML(1+10); DS2603-2
	@Temperature 121 Â°C	@Temperature 250 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 11.5 MPa	>= 1670 psi	
	>= 9.50 MPa	>= 1380 psi	
Elongation at Break	@Temperature 275 Â°C, Time 86400 sec	@Temperature 527 Â°F, Time 24.0 hour	
	>= 160 %	>= 160 %	
Compression Set	>= 130 %	>= 130 %	AF compression rate 30%
	@Temperature 275 Â°C, Time 86400 sec	@Temperature 527 Â°F, Time 24.0 hour	
	<= 25 %	<= 25 %	
	@Temperature 200 Â°C, Time 86400 sec	@Temperature 392 Â°F, Time 24.0 hour	

Descriptive Properties	Value	Comments
Appearance	White or light yellow translucent rubber piece	

Descriptive Properties	Value	Comments (fuel, 200Å°C, 24h, added weight)
------------------------	-------	--

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China