

Shandong Rike Chemical HELI,ç HL-2005 Weather-resistance Acrylic Impact Modifier (AIM)

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer

Material Notes:

Outline of ACR Impact Modifiers: The PVC impact modifiers developed by our company are acrylic copolymers (ACR) with a core-shell structure, their cores are acrylic ester and shells are methacrylic copolymers. The basic functions of our impact modifiers are to improve the impact performance of PVC products to meet the requirements of engineering plastics and simultaneously increase their heat and light stability. Information Provided by Shandong Rike Chemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shandong-Rike-Chemical-HELI-HL-2005-Weather-resistance-Acrylic-Impact-Modifier-AIM.php

Mechanical Properties	Metric	English	Comments
Izod Impact, Unnotched (ISO)	14.6 kJ/m ²	6.95 ft-lb/in ²	Phr = 0
	@Temperature 0.000 Å°C	@Temperature 32.0 Å°F	
	19.1 kJ/m ²	9.09 ft-lb/in ²	Phr = 5
	@Temperature 0.000 Å°C	@Temperature 32.0 Å°F	
	19.7 kJ/m ²	9.37 ft-lb/in ²	Phr = 0
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
	25.3 kJ/m ²	12.0 ft-lb/in ²	Phr = 8
	@Temperature 0.000 Å°C	@Temperature 32.0 Å°F	
	34.7 kJ/m ²	16.5 ft-lb/in ²	Phr = 5
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
	37.1 kJ/m ²	17.7 ft-lb/in ²	Phr = 8
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	84.6 Å°C	184 Å°F	Phr = 8
	86.0 Å°C	187 Å°F	Phr = 0

Descriptive Properties	Value	Comments
Light Aging - Whiteness Variation (%)	15.3	Phr = 8

Descriptive Properties	Value	Comments
	51.22	Phr = 0
Thermal Aging - Whiteness Variation (%)	20.4	Phr = 0
	26.8	Phr = 5
	31.1	Phr = 8

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China