

Shandong Rike Chemical HELIâ, ¢ HLC-40B PVC Impact Modifier-CPE Series

Category: Other Engineering Material, Additive/Filler for Polymer, Polymer, Thermoplastic, Polyethylene (PE)

Material Notes:

Mechanism of Impact ModificationIt is found by research that the weak impact strength of PVC under lower temperature is mainly caused by stronger intermolecular force of PVC. Owing to stronger intermolecular force, when PVC products are impacted, the relative displacement between PVC molecules is hard to take place, thus impact energy can not be effectively transferred into internal friction heat, resulting in the breaking of PVC materials. But owing to higher glass temperature and worse dispersibility of CPE, thus low temperature impact strength of CPE is not ideal. Moreover, due to heat stabilizers in PVC blend can not permeate into CPE, therefore CPE which is filled in PVC compound is easy to decompose, so that the heat stability of PVC products modified by CPE is worse. Thus, the key questions to improve the PVC impact strength is how to largely reduce the PVC intermolecular force and so that increasing the speed that the PVC impact energy transfers into the heat energy.Information Provided by Shandong Rike Chemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shandong-Rike-Chemical-HELI-HLC-40B-PVC-Impact-Modifier-CPE-Series.php

Physical Properties	Metric	English	Comments
Bulk Density	0.400 - 0.600 g/cc	0.0145 - 0.0217 lb/in³	
Volatiles	<= 0.40 %	<= 0.40 %	
Particle Size	900 µm	900 µm	<2%

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	<= 57	<= 57	
Tensile Strength	6.00 MPa	870 psi	

Component Elements Properties	Metric	English	Comments	
Chlorine, Cl	38 - 42 %	38 - 42 %		

Descriptive Properties	Value	Comments
Appearance	White powder	
Colored Particles (Pcs/100g)	<60	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058



Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China