

## Shanghai Ofluorine 9202F PVDF Powder for cables

Category : Polymer , Thermoplastic , Fluoropolymer , PVDF

**Material Notes:**

Description: Excellent mechanical properties, heat resistance and flame resistance, PVDF for cable can bear high temperature, corrosive chemicals etc harsh working environment, which has low smoke, low fog, low flame spread characteristics. Information provided by Shanghai Ofluorine Chemical Technology

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Shanghai-Ofluorine-9202F-PVDF-Powder-for-cables.php](http://www.lookpolymers.com/polymer_Shanghai-Ofluorine-9202F-PVDF-Powder-for-cables.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.77 - 1.78 g/cc	1.77 - 1.78 g/cc	ISO R1183D
Particle Size	<= 30 Åµm	<= 30 Åµm	Average size before sieving
Melt Flow	2.0 - 6.0 g/10 min @Load 5.00 kg, Temperature 230 Å°C	2.0 - 6.0 g/10 min @Load 11.0 lb, Temperature 446 Å°F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	68	68	ISO 868
Tensile Strength at Break	>= 26.0 MPa @Strain >=100 %	>= 3770 psi @Strain >=100 %	ISO R527
Elongation at Break	>= 100 %	>= 100 %	ISO R527
Flexural Strength	680 MPa	98600 psi	ISO 178
Izod Impact, Notched	8.00 J/cm	15.0 ft-lb/in	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	141 - 144 Å°C	286 - 291 Å°F	ISO 416C
Heat Distortion Temperature	48.0 Å°C	118 Å°F	ISO 75
Oxygen Index	43 %	43 %	ASTM D2863

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China