

Sharadaa Ceramics PCF60-1 Precast Prefired Brick

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Features: Manufactured under controlled conditions under refractory engineers supervision; Measured Quantity/Temperature of water, mixing by Intensive counter current mixers, Forming by Vibro Casting techniques and Pre-fired up to 1450Â°. Elimination of Casting defects, cracks and voids. Evidencing the Guaranteed data sheet values in the final product. Application Areas: Steel: Well Blocks, Nozzles, EAF Roof, Launderers, Impact Pad, Darts Tundish Flow Control Devices, and Lances Reheat/Forging furnaces: Hearth Blocks, Burner Blocks Ferrous/Non-Ferrous: Launderers, Ladles, Doors, Impact Resistant Blocks Petro Chemical: Re-generator Tiles, Mullite Burner Blocks Furnaces: Liner Tiles enabling longer life of Refractories. Information provided by Sharadaa Ceramics Pvt. Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sharadaa-Ceramics-PCF60-1-Precast-Prefired-Brick.php

Physical Properties	Metric	English	Comments
Bulk Density	2.60 g/cc	0.0939 lb/inÂ³	After Drying at 110Â°C
Porosity	16 %	16 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	137 MPa	19900 psi	Cold Crushing

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1550 Â°C	2820 Â°F	

Component Elements Properties	Metric	English	Comments
Al2O3	>= 60 %	>= 60 %	
Fe2O3	<= 1.5 %	<= 1.5 %	

Descriptive Properties	Value	Comments
Permanent Linear Change	-1.0 - 1.0%	1450Â°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China