

## Sharadaa Ceramics REFCAST NORMAL Dense Castables

Category : Ceramic

### Material Notes:

Description: We offer a range of Dense Castables that are conventional castable and extensively used in boiler work, general furnace and burner blocks. Made as per international standards, our range is known for its high strength, low thermal conductivity and requires less maintenance. Information provided by Sharadaa Ceramics Pvt. Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sharadaa-Ceramics-REFCAST-NORMAL-Dense-Castables.php](http://www.lookpolymers.com/polymer_Sharadaa-Ceramics-REFCAST-NORMAL-Dense-Castables.php)

Physical Properties	Metric	English	Comments
Bulk Density	>= 2.00 g/cc	>= 0.0723 lb/in <sup>3</sup>	Sample, cast, cured, dried at 110 <sup>o</sup> C
Grain Size	<= 5000 $\mu$ m	<= 5000 $\mu$ m	

Mechanical Properties	Metric	English	Comments
Compressive Strength	24.5 MPa	3560 psi	Cold Crushing
	@Temperature 1100 $\text{^{\circ}}$ C	@Temperature 2010 $\text{^{\circ}}$ F	
	34.3 MPa	4980 psi	Cold Crushing
	@Temperature 110 $\text{^{\circ}}$ C	@Temperature 230 $\text{^{\circ}}$ F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1300 $\text{^{\circ}}$ C	2370 $\text{^{\circ}}$ F	

Component Elements Properties	Metric	English	Comments
Al <sub>2</sub> O <sub>3</sub>	>= 45 %	>= 45 %	
Fe <sub>2</sub> O <sub>3</sub>	<= 5.0 %	<= 5.0 %	

Processing Properties	Metric	English	Comments
Moisture Content	12 - 14 %	12 - 14 %	

Descriptive Properties	Value	Comments
Permanent Linear Change	-1.0 - 1.0%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China