

Sharadaa Ceramics REFINSUL ZAP-016 Insulating Castables

Category : Ceramic

Material Notes:

Description: We provide our clients a range of Insulating Castables, that are used as backup layer in process industries and hot face layer in petrochemical industry. These castables are known for low density and low thermal conductivity, and are helpful in conserving heat energy thus reducing fuel costs. Information provided by Sharadaa Ceramics Pvt. Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sharadaa-Ceramics-REFINSUL-ZAP-016-Insulating-Castables.php

Physical Properties	Metric	English	Comments
Bulk Density	<= 1.10 g/cc	<= 0.0397 lb/in ³	Dried at 110 ^o C

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.00118 GPa	0.171 ksi	Dried at 110 ^o C
	0.000490 GPa	0.0711 ksi	
	@Treatment Temp. 1100 ^o C	@Treatment Temp. 2010 ^o F	
Compressive Strength	0.000588 GPa	0.0853 ksi	
	@Treatment Temp. 800 ^o C	@Treatment Temp. 1470 ^o F	
Compressive Strength	1.18 MPa	171 psi	Fired at Service temp. of 1100 ^o C, Cold Crushing
	1.47 MPa	213 psi	Fired at 800 ^o C, Cold Crushing
	1.96 MPa	284 psi	Dried at 110 ^o C, Cold Crushing

Thermal Properties	Metric	English	Comments
Thermal Conductivity	<= 0.256 W/m-K	<= 1.78 BTU-in/hr-ft ² - ^o F	
	@Temperature 500 ^o C	@Temperature 932 ^o F	

Component Elements Properties	Metric	English	Comments
Al2O3	>= 32 %	>= 32 %	
Fe2O3	<= 6.0 %	<= 6.0 %	

Descriptive Properties	Value	Comments
Permanent Linear Change	-0.8 - 0.8%	Fired at 800 ^o C

Descriptive Properties

Value 1.2%

Comments vice temp. 1100Å°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China