

Sharadaa Ceramics Sharada RFC-LW Gel Bonded Castables

Category : Ceramic

Material Notes:

Mullite Bonded Free Flowing Cement Free Versatile Castable System
 Product Characteristics: High Mullitisation, Free from Low Temperature eutectics, Non wetting to molten metals Ferrous/Non Ferrous, Extreme resistance to thermal, Ultra high creep resistance-High HMOR, Intricate shaped Precast blocks superior to fired and Resistance to Mill scale /Accretion
 Industry Focus: Steel: Blast Furnace Trough, Torpedo Ladles, Lances/Snorkel, Burner Blocks, Reheat furnace roof/Hearth, Coke Oven door/ Roof Repair, Sponge Iron DRI Maintenance, Tundish Flow control device/Well blocks/Nozzles; Cement: Burner Pipe; Non Ferrous: Non wetting to Aluminum/Copper, Lined in Melting furnace walls, Launderers, Aluminum Transfer Ladles; Ceramic: Fused silica kiln furniture for Ultra Low thermal, Expansion and High resistance to thermal shock; Ferrous Foundry: Ladles; Glass: Repair of Silica Roof, Sub paving.
 Information provided by Sharadaa Ceramics Pvt. Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sharadaa-Ceramics-Sharada-RFC-LW-Gel-Bonded-Castables.php

Physical Properties	Metric	English	Comments
Bulk Density	1.40 g/cc	0.0506 lb/in ³	
	@Temperature 1400 °C	@Temperature 2550 °F	
	1.45 g/cc	0.0524 lb/in ³	
	@Temperature 800 °C	@Temperature 1470 °F	
Porosity	1.50 g/cc	0.0542 lb/in ³	
	@Temperature 200 °C	@Temperature 392 °F	
	38 %	38 %	
	40 %	40 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	0.981 MPa	142 psi	
	@Temperature 1400 °C	@Temperature 2550 °F	Cold Crushing
	8.83 MPa	1280 psi	
	@Temperature 800 °C	@Temperature 1470 °F	Cold Crushing

Component Elements Properties	Metric	English	Comments
Al2O3	40 %	40 %	

Component Elements Properties	Metric	English	Comments
Descriptive Properties			
Base Material	Insulation Aggregate		
Permanent Linear Change	-1.0 - 1.0%		1400°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China