

## Shin-Etsu Silicones KE-1052A/B Silicone, Gel RTV

Category : Polymer , Thermoset , Silicone

**Material Notes:**

Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Shin-Etsu-Silicones-KE-1052AB-Silicone-Gel-RTV.php](http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-KE-1052AB-Silicone-Gel-RTV.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.990 g/cc	0.990 g/cc	
Viscosity	1000 cP	1000 cP	

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	65	65	

Electrical Properties	Metric	English	Comments
Dielectric Strength	20.0 kV/mm	508 kV/in	
Dissipation Factor	0.00020 @Frequency 60.0 Hz	0.00020 @Frequency 60.0 Hz	

Processing Properties	Metric	English	Comments
Cure Time	1440 min @Temperature 23.0 Â°C	24.0 hour @Temperature 73.4 Â°F	

Descriptive Properties	Value	Comments
Colors	Clear	
Mix Ratio By Weight	1:01	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China