

Shin-Etsu Silicones KE-3470 Silicone, RTV Conformal Coating

Category : Polymer , Thermoset , Silicone

Material Notes:

Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-KE-3470-Silicone-RTV-Conformal-Coating.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.00 g/cc	1.00 g/cc	
Viscosity	60 cP	60 cP	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	
Tensile Strength at Break	0.345 MPa	50.0 psi	
Shear Strength	0.138 MPa	20.0 psi	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² - Â°F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	25.0 kV/mm	635 kV/in	
Dissipation Factor	0.00010 @Frequency 60.0 Hz	0.00010 @Frequency 60.0 Hz	

Processing Properties	Metric	English	Comments
Cure Time	5.00 min	0.0833 hour	Tack Free Time
	4320 min @Temperature 23.0 Â°C	72.0 hour @Temperature 73.4 Â°F	50% RH

Descriptive Properties	Value	Comments
Colors	Transparent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China