

Shin-Etsu Silicones KE-441 Silicone, RTV

Category : Polymer , Thermoset , Silicone

Material Notes:

Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-KE-441-Silicone-RTV.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	
Viscosity	15000 cP	15000 cP	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	15	15	
Tensile Strength	1.70 MPa	247 psi	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.210 W/m-K	1.46 BTU-in/hr-ft ² - °F	

Electrical Properties	Metric	English	Comments
Dissipation Factor	0.0050	0.0050	
	@Frequency 50.0 Hz	@Frequency 50.0 Hz	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	Tack Free Time

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China