

Shin-Etsu Silicones KE-45 Silicone, RTV

Category : Polymer , Thermoset , Silicone

Material Notes:

Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-KE-45-Silicone-RTV.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	
Tensile Strength	2.00 MPa	290 psi	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.210 W/m-K	1.46 BTU-in/hr-ft ² - °F	

Electrical Properties	Metric	English	Comments
Dissipation Factor	0.0050 @Frequency 50.0 Hz	0.0050 @Frequency 50.0 Hz	

Processing Properties	Metric	English	Comments
Cure Time	6.00 min	0.100 hour	Tack Free Time

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China