

## Shin-Etsu Silicones KE-581U Silicone Elastomer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

### Material Notes:

KE581U is one of a series of easy processing, general purpose grade silicone rubber bases. It can be used in a variety of applications requiring finishing by molding or extruding with extending filler. Product Features: This product can be blended with KE541U, KE551U, KE561U, and KE571U for intermediate hardnesses. The choice between these bases will depend on specific requirements. Typical Applications: Roll covers. Diaphragms. O-rings and gaskets. Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Shin-Etsu-Silicones-KE-581U-Silicone-Elastomer.php](http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-KE-581U-Silicone-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	DCBP Cure
	1.24 g/cc	1.24 g/cc	DBPH Cure

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78	78	DCBP Cure
	78	78	DBPH Cure
Tensile Strength at Break	10.31 MPa	1495 psi	DBPH Cure
	11.20 MPa	1625 psi	DCBP Cure
Elongation at Break	350 %	350 %	DCBP Cure
	360 %	360 %	DBPH Cure
Tear Strength	12.1 kN/m	69.0 pli	Die B; DCBP Cure
	13.0 kN/m	74.0 pli	Die B; DBPH Cure
Compression Set	23 %	23 %	DCBP Cure
	@Temperature 150 Å°C, Time 79200 sec	@Temperature 302 Å°F, Time 22.0 hour	

Descriptive Properties	Value	Comments
Cure Agent	DBPH	
	DCBP	
Cure Type	Post Cure	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China