

Shin-Etsu Silicones KE-931U Silicone Elastomer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

KE931 U is one of a series of easy processing, general purpose silicone rubber bases. It can be used in a variety of applications requiring finishing by molding (compression, injection, transfer). Product Features: Rubber contacts. Food packing. Industrial packing. Diaphragms. Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-KE-931U-Silicone-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	
Tensile Strength at Break	5.38 MPa	780 psi	
Elongation at Break	570 %	570 %	
Tear Strength	9.82 kN/m	56.0 pli	Die B
Compression Set	15 % @Temperature 180 Â°C, Time 79200 sec	15 % @Temperature 356 Â°F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	240 min @Temperature 200 Â°C	4.00 hour @Temperature 392 Â°F	Post

Descriptive Properties	Value	Comments
Cure Agent	DBPH	
Cure Type	Post Cure	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China