

Shin-Etsu Silicones LIMSâ„† KE2090-30AB Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

KE-2090-30 is a selective self-adhesive liquid injection molding silicone. It is supplied as two components which are mixed in a 1:1 ratio to ensure easy and accurate blending. Its viscosity is low enough to allow easy pumping through most injection molding systems. Features Selective self adhesion Non adhesion to metals Insert-molding and co-injection molding available Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-LIMS-KE2090-30AB-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.11 g/cc	1.11 g/cc	
Viscosity	400000 cP	400000 cP	A
	800000 cP	800000 cP	B
Linear Mold Shrinkage	0.022 cm/cm	0.022 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	
Tensile Strength	8.50 MPa	1230 psi	
Elongation at Yield	840 %	840 %	
Tear Strength	25.0 kN/m	143 pli	
Compression Set	7.0 %	7.0 %	
	@Temperature 200 Â°C, Time 14400 sec	@Temperature 392 Â°F, Time 4.00 hour	
	25 %	25 %	
	@Temperature 150 Â°C, Time 3600 sec	@Temperature 302 Â°F, Time 1.00 hour	

Processing Properties	Metric	English	Comments
Cure Time	10.0 min	0.167 hour	Press Cure
	@Temperature 120 Â°C	@Temperature 248 Â°F	

Descriptive Properties	Value	Comments
Appearance	Translucent	

<small>Cure Rate</small> Descriptive Properties	<small>47</small> Value	<small>T10 (248Å°F, ODR)</small> Comments
	62	T90 (248Å°F, ODR)
Regulatory Testing	Class VI	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China