

## Shin-Etsu Silicones LIMSâ„¢ KEG2001-40A/B Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

KEG2001-40 is a very fast cure type liquid injection molding silicone. It is supplied as two components which are mixed in a 1:1 ratio to ensure easy and accurate blending. Its viscosity is low enough to allow easy pumping through most injection molding systems. Features High tear strength Rapid cure time at elevated temperature Long pot life at room temperature Applications O-Rings Diaphragms Capping Rubber rollers Connector packaging Other electrical parts Information Provided by Shin-Etsu Silicones of America, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Shin-Etsu-Silicones-LIMS-KEG2001-40AB-Elastomer.php](http://www.lookpolymers.com/polymer_Shin-Etsu-Silicones-LIMS-KEG2001-40AB-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	
Viscosity	1.20e+6 cP	1.20e+6 cP	B
	1.40e+6 cP	1.40e+6 cP	A
Linear Mold Shrinkage	0.027 cm/cm	0.027 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	
Tensile Strength	11.0 MPa	1600 psi	
Elongation at Yield	700 %	700 %	
100% Modulus	0.00125 GPa	0.182 ksi	
Tear Strength	33.0 kN/m	188 pli	
Compression Set	6.0 %	6.0 %	
	@Temperature 200 Â°C, Time 14400 sec	@Temperature 392 Â°F, Time 4.00 hour	
Compression Set	33 %	33 %	
	@Temperature 150 Â°C, Time 3600 sec	@Temperature 302 Â°F, Time 1.00 hour	

Processing Properties	Metric	English	Comments
Cure Time	5.00 min	0.0833 hour	Press Cure
	@Temperature 150 Â°C	@Temperature 302 Â°F	
Cure Time	60.0 min	1.00 hour	Post Cure
	@Temperature 150 Â°C	@Temperature 302 Â°F	

Processing Properties	Metric	English	Comments
Descriptive Properties		Value	Comments
Appearance		Translucent	
Cure Rate		24	T10 (302°F, ODR)
		33	T90 (302°F, ODR)

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China