

Shinil Chemical SHINCON PETG Electro Conductive Polymer

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , PETG Copolyester

Material Notes:

SHINCON is the product line of SHINIL's electrically conductive compound which is able to dissipate the electrostatic charge (ESD) effectively. Shinil has developed SHINCON products using Shinil's patented conductive filler dispersion technology with variety of engineering polymers and their alloys to impart permanent static dissipative to electrically conductive property to thermoplastics. SHINCON contains multiwall carbon nanotube (MWCNT), carbon black (CB), and carbon fiber (CF) as a conductive filler. SHINCON are used in injection molding, film or sheet extrusion for the applications where the desired level of conductivity and unique mechanical property are important. A wide range of the surface resistivity is obtained by SHINCON formulations for the parts and devices depending upon customer needs and applications.

Feature and Benefits

- Permanent electro conductivity
- Maintain the physical properties of base resin
- No particulates (CNT product)
- Lighter weight
- Recyclability
- Easy processing
- Improved surface
- Cost effective
- Module tray

Information Provided by Shinil Chemical Industry Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shinil-Chemical-SHINCON-PETG-Electro-Conductive-Polymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.28 g/cc	1.28 g/cc	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	49.0 MPa	7110 psi	
Flexural Strength	73.575 MPa	10671 psi	
Flexural Modulus	2.26 GPa	327 ksi	
Izod Impact, Notched	0.392 J/cm	0.735 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	70.0 Â°C	158 Â°F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.00e+6 ohm-cm	3.00e+6 ohm-cm	

Processing Properties	Metric	English	Comments
Processing Temperature	230 Â°C	446 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China