

Shinil Chemical SHINNANO PP Polymer Nanocomposite Bumper

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

SHINNANO is the product line of polymer nanocomposite made by dispersing nano fillers, mainly, NANOCLAY. Recently, Shinil has developed various nanocomposite grades for automotive applications using Shinil's proprietary dispersion technology combined with the customized nanoclay. Shinil's SHINNANO offers unique properties compared to conventional polymer compounds. Nanocomposite products of SHINNANO provide not only high performance but also the lighter weight (10-20%). SHINNANO uses various engineering polymers to produce functional nanocomposite grades. Nanoclays are incorporated during the melt compounding. The clay particles are exfoliated during processing, which leads to nano-size platelets. Although this process is challenging, owing to unique dispersion technique that is developed for nano materials, Shinil produces high performance nanocomposites with less use of nano fillers. SHINNANO grades are available for automotive parts such as bumper, instrument panel, door trim, engine cover, cylinder head cover, and air intake manifold.

Feature and Benefits
 Lighter weight
 High stiffness
 High HD
 High modulus
 Improved surface
 Improved melt strength
 Recyclability
 Available for injection molding, extrusion or film making
 Cost effective
 Good barrier property

Information Provided by Shinil Chemical Industry Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shinil-Chemical-SHINNANO-PP-Polymer-Nanocomposite-Bumper.php

Physical Properties	Metric	English	Comments
Specific Gravity	<= 1.00 g/cc	<= 1.00 g/cc	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	19.6 MPa	2840 psi	
Elongation at Break	100 %	100 %	
Flexural Strength	29.43 MPa	4268 psi	
Flexural Modulus	1.86 GPa	270 ksi	
Izod Impact, Notched	NB	NB	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	125 Â°C	257 Â°F	

Processing Properties	Metric	English	Comments
Processing Temperature	210 Â°C	410 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China