

Shinkong Synthetic Fibers Shinite® D201G30 PBT, 30% Glass Filled

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

Material Notes:

Information from Shinkong Synthetic Fibers Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shinkong-Synthetic-Fibers-Shinite-D201G30-PBT-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.52 g/cc	1.52 g/cc	ASTM D792
Water Absorption	0.070 %	0.070 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0050 - 0.0090 cm/cm	0.0050 - 0.0090 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	123 MPa	17800 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Yield Strength	206 MPa	29900 psi	ASTM D790
Flexural Modulus	8.83 GPa	1280 ksi	ASTM D790
Izod Impact, Notched	0.981 J/cm @Thickness 3.17 mm, Temperature 23.0 °C	1.84 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	ASTM D257
Dielectric Constant	4.0	4.0	ASTM D150
Dielectric Strength	27.0 kV/mm	686 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China