

## Shinkong Synthetic Fibers Shinite<sup>®</sup> D202G30 PBT, 30% Glass Filled, Fire Retardant

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled , Polybutylene Terephthalate (PBT), Flame Retardant

### Material Notes:

Information from Shinkong Synthetic Fibers Corp.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Shinkong-Synthetic-Fibers-Shinite-D202G30-PBT-30-Glass-Filled-Fire-Retardant.php](http://www.lookpolymers.com/polymer_Shinkong-Synthetic-Fibers-Shinite-D202G30-PBT-30-Glass-Filled-Fire-Retardant.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.62 g/cc	1.62 g/cc	ASTM D792
Water Absorption	0.070 %	0.070 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0050 - 0.0090 cm/cm	0.0050 - 0.0090 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	127 MPa	18500 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Yield Strength	191 MPa	27700 psi	ASTM D790
Flexural Modulus	9.32 GPa	1350 ksi	ASTM D790
Izod Impact, Notched	0.883 J/cm @Thickness 3.17 mm, Temperature 23.0 Å°C	1.65 ft-lb/in @Thickness 0.125 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	210 Å°C	410 Å°F	ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Constant	4.0	4.0	ASTM D150
Dielectric Strength	23.0 kV/mm	584 kV/in	ASTM D149

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**