

## Shinkong Synthetic Fibers Shinite® E202G15 PBT, 15% Glass Filled

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

**Material Notes:**

Information from Shinkong Synthetic Fibers Corp.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Shinkong-Synthetic-Fibers-Shinite-E202G15-PBT-15-Glass-Filled.php](http://www.lookpolymers.com/polymer_Shinkong-Synthetic-Fibers-Shinite-E202G15-PBT-15-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792
Water Absorption	0.070 %	0.070 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0050 - 0.0090 cm/cm	0.0050 - 0.0090 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	90.2 MPa	13100 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Yield Strength	144 MPa	20900 psi	ASTM D790
Flexural Modulus	5.49 GPa	797 ksi	ASTM D790
Izod Impact, Notched	0.539 J/cm @Thickness 3.17 mm, Temperature 23.0 Å°C	1.01 ft-lb/in @Thickness 0.125 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	205 Å°C	401 Å°F	ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Constant	3.0	3.0	ASTM D150
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China