Sibur 1030-13 Compound OMN Polyvinyl Chloride (PVC)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

Material Notes:

Shall correspond to control sample, approved in accordance with the established procedure. Pores, which can be seen by eyes, are not allowed. Plastic shall no burn at stop of worm extruder for a period of 20 minutes. For insulation of wires and cables operating in intervals of temperatures from -40ŰC to 70ŰC.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sibur-1030-13-Compound-OMN-Polyvinyl-Chloride-PVC.php

Physical Properties	Metric	English	Comments
Density	1.45 - 1.55 g/cc	0.0524 - 0.0560 lb/in³	
Water Absorption	<= 0.40 %	<= 0.40 %	
Collected Volatile Condensable Material	<= 2.5 %	<= 2.5 %	Loss in mass at 160°C during 6 hours

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 15.0 MPa	>= 2180 psi	
Elongation at Break	>= 200 %	>= 200 %	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -30.0 °C	<= -22.0 °F	
Decomposition Temperature	>= 200 °C	>= 392 °F	Thermal stability, for 80 minutes
Flammability Test	<= 15	<= 15	In seconds, method A

Electrical Properties	Metric	English	Comments
	>= 5.00e+10 ohm-cm	>= 5.00e+10 ohm-cm	
Volume Resistivity	@Temperature 70.0 °C	@Temperature 158 °F	
	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Descriptive Properties	Value	Comments
Color	Non-colored, black	



Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China