

## Sibur 21080-PM1 Polypropylene with Low Haze

Category: Polymer, Thermoplastic, Polypropylene (PP), Polypropylene, Molded

**Material Notes:** 

For production of three-layer PE/PP film, for production of sheets for cups and thin casting. It is allowed for contact with food products.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Sibur-21080-PM1-Polypropylene-with-Low-Haze.php

Physical Properties	Metric	English	Comments
Melt Index of Compound	5.0 - 10 g/10 min	5.0 - 10 g/10 min	
Collected Volatile Condensable Material	<= 0.12 %	<= 0.12 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 26.0 MPa	>= 3770 psi	
Modulus of Elasticity	>= 1.20 GPa	>= 174 ksi	Bending
Izod Impact, Notched (ISO)	>= 3.00 kJ/m²	>= 1.43 ft-lb/in²	
	@Temperature 0.000 °C	@Temperature 32.0 °F	

Descriptive Properties	Value	Comments
Muddiness of Film	<25%	
Spread Flow Batch Error	<±15 %	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China