

## Sibur 23007-30T 1st Grade Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

**Material Notes:**

For production of pipes for hot and cold water supply, sewerage, containers for shampoo, oil, milk, and packing products of low muddiness.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sibur-23007-30T-1st-Grade-Polypropylene-Copolymer.php](http://www.lookpolymers.com/polymer_Sibur-23007-30T-1st-Grade-Polypropylene-Copolymer.php)

Physical Properties	Metric	English	Comments
Melt Index of Compound	0.20 - 0.90 g/10 min	0.20 - 0.90 g/10 min	
Ash	<= 0.045 %	<= 0.045 %	For compounding of stabilization of 16M and painted marks are not normalized
Collected Volatile Condensable Material	<= 0.15 %	<= 0.15 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 22.0 MPa	>= 3190 psi	
Elongation at Break	>= 400 %	>= 400 %	

Descriptive Properties	Value	Comments
Number of Inclusions	<10 pcs	
Spread Flow Batch Error	<±20 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China