

## Sibur ABS 2020-30M Molding Grade ABS Plastic

Category: Polymer, Thermoplastic, ABS Polymer, Acrylonitrile Butadiene Styrene (ABS), Molded

## **Material Notes:**

With high thermal and light resistance for automobile building, stable to atmospheric conditions in thermal and electric ageing, contacting with food products, as well as with compounding with PC.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Sibur-ABS-2020-30M-Molding-Grade-ABS-Plastic.php

Physical Properties	Metric	English	Comments
Melt Index of Compound	12 - 14 g/10 min	12 - 14 g/10 min	

Mechanical Properties	Metric	English	Comments
Elongation at Break	>= 20 %	>= 20 %	
Izod Impact, Notched (ISO)	>= 20.0 kJ/m²	>= 9.52 ft-lb/in²	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	<= 97.0 °C	<= 207 °F	

Descriptive Properties	Value	Comments
Impact Tension Strength	>20 MPa	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China