

## Sibur BK-1675S Butyl Rubber (IIR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

**Material Notes:**

EXXON Butyl 268, PB 301 Bayer. For use in the construction industry.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sibur-BK-1675S-Butyl-Rubber-IIR.php](http://www.lookpolymers.com/polymer_Sibur-BK-1675S-Butyl-Rubber-IIR.php)

Physical Properties	Metric	English	Comments
Mooney Viscosity	35 - 65 @Temperature 100 Â°C	35 - 65 @Temperature 212 Â°F	ML 1-4

Descriptive Properties	Value	Comments
Loss During Drying	<0.5%	
Spread Flow Batch Error	<Â±8 %	
Unsaturation	0.7-2.3%, mol	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China