

## Sibur BSK1502 Styrene-Butadiene Rubber (SBR)

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

## **Material Notes:**

SBR-1502. For use in the tire industry for production of tire thread and other parts for tires, in rubber technical industry for production of a wide assortment of rubber technical articles, and in the shoe industry for production of white and colored rubber footwear.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Sibur-BSK1502-Styrene-Butadiene-Rubber-SBR.php

Physical Properties	Metric	English	Comments	
Mooney Viscosity	45 - 57	45 - 57	ML 1-4	
	@Temperature 100 °C	@Temperature 212 °F	WL 1-4	
Ash	<= 0.60 %	<= 0.60 %		

Chemical Properties	Metric	English	Comments
Styrene Content	21 - 24 %	21 - 24 %	

Descriptive Properties	Value	Comments
Loss During Drying	<0.5%	
Mass Share of Trinonilphenilephosphite	1-2%	
Mass Share of Vingstay T	0.7-2%	
Spread Flow Batch Error	<±8 %	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China