

## Sibur DST-30-01 1st Group Styrene-Butadiene-Styrene Block Copolymer (SBS-TPE)

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrene-Butadiene , Styrene/Butadiene/Styrene (SBS)

### Material Notes:

Kraton D 1101, 1102. For modification of bitumen, intended for road coverings, modification of plastics, and for production of glues, strip hermetic, and protective coatings.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sibur-DST-30-01-1st-Group-Styrene-Butadiene-Styrene-Block-Copolymer-SBS-TPE.php](http://www.lookpolymers.com/polymer_Sibur-DST-30-01-1st-Group-Styrene-Butadiene-Styrene-Block-Copolymer-SBS-TPE.php)

Physical Properties	Metric	English	Comments
Ash	<= 5.0 %	<= 5.0 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 19.6 MPa	>= 2840 psi	
Elongation at Break	>= 650 %	>= 650 %	

Descriptive Properties	Value	Comments
Loss During Drying	<0.5%	
Mass Share Adigol-2	0.5-1%	
Mass Share Agidol-1	0.2-0.5%	
Mass Share of Non-Polymerized Styrene	<0.02%	
Mass Share of VS-38	0.5-1%	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China