

## Sibur Nitrilast-26M Nitrile-Butadiene Rubber (NBR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

2845 N 28.60. For production of oil-benzene resistant articles for the automobile, aviation and rubber technical industries. Rubbers on the base of Nitrilast possess good oil-benzene resistance. Rubber mixtures on the base of Nitrilast are more resistant to wearing than those made of natural rubber.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sibur-Nitrilast-26M-Nitrile-Butadiene-Rubber-NBR.php](http://www.lookpolymers.com/polymer_Sibur-Nitrilast-26M-Nitrile-Butadiene-Rubber-NBR.php)

Physical Properties	Metric	English	Comments
Mooney Viscosity	43 - 68 @Temperature 100 Â°C	43 - 68 @Temperature 212 Â°F	ML 1-4
Ash	<= 0.60 %	<= 0.60 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 23.5 MPa	>= 3410 psi	
Elongation at Break	>= 450 %	>= 450 %	

Descriptive Properties	Value	Comments
Loss During Drying	0.01	
Mass Share Adigol-2	0.5-1.2%	
Mass Share of VS-30A	1-1.5%	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China