

Sibur PVC S-7059-M Suspension Polyvinyl Chloride (PVC)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

For production of articles by methods of extrusion, calendaring, pressing, rolling, or molding under pressure.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sibur-PVC-S-7059-M-Suspension-Polyvinyl-Chloride-PVC.php

Physical Properties	Metric	English	Comments
Density	0.450 - 0.550 g/cc	0.0163 - 0.0199 lb/in ³	
Collected Volatile Condensable Material	<= 0.30 %	<= 0.30 %	Moisture and volatile matters

Thermal Properties	Metric	English	Comments
Decomposition Temperature	>= 160 Â°C	>= 320 Â°F	Thermal stability, for 10 minutes

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 5.00e+13 ohm-cm	>= 5.00e+13 ohm-cm	

Descriptive Properties	Value	Comments
K-Value	70-73	
Mass Share of Vinyl Chloride, mIn-1	>10	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China