

## Sibur SKI-3 1st Grade, 2nd Group Isoprene Rubber (IR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

**Material Notes:**

Nipol-IR 2200, Natsyn-2200, Kraton-IR 401. For production of tires and rubber technical articles of wide assortment.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sibur-SKI-3-1st-Grade-2nd-Group-Isoprene-Rubber-IR.php](http://www.lookpolymers.com/polymer_Sibur-SKI-3-1st-Grade-2nd-Group-Isoprene-Rubber-IR.php)

Physical Properties	Metric	English	Comments
Mooney Viscosity	65 - 74 @Temperature 100 Â°C	65 - 74 @Temperature 212 Â°F	ML 1-4
Ash	<= 0.50 %	<= 0.50 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 28.4 MPa	>= 4120 psi	
Tensile Strength, Ultimate	>= 19.6 MPa @Temperature 100 Â°C	>= 2840 psi @Temperature 212 Â°F	

Descriptive Properties	Value	Comments
Loss During Drying	<0.6%	
Mass Share of Anti-oxidants	0.2-0.3%	
Mass Share VTS-60	0.35-0.55%	
Spread Flow Batch Error	<Â±8 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China