

Sibur SKS-30 ARK 1st Grade Styrene-Butadiene Rubber (SBR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

SBR-1500. For use in the shoe industry and for production of vulcanized micro-porous sole rubbers and rubber technical articles.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sibur-SKS-30-ARK-1st-Grade-Styrene-Butadiene-Rubber-SBR.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	45 - 57 @Temperature 100 Â°C	45 - 57 @Temperature 212 Â°F	ML 1-4
Ash	<= 0.60 %	<= 0.60 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 26.0 MPa	>= 3770 psi	
Elongation at Break	550 - 750 %	550 - 750 %	

Chemical Properties	Metric	English	Comments
Styrene Content	22.5 - 24.5 %	22.5 - 24.5 %	

Descriptive Properties	Value	Comments
Loss During Drying	<0.35%	
Mass Share Adigol-2	0.7-1.2%	
Mass Share of A-Methyl Styrene	22-25%	
Mass Share of P-23	0.4-1.2%	
Mass Share of VS-30A	1-2%	
Mass Share of VTS-150	1-1.4%	
Spread Flow Batch Error	<Â±6 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China