

Sibur SKS-30 ARKPN 1st Group Styrene-Butadiene Rubber (SBR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

SBR-1502. For use in the tire industry for production of tire thread and other parts for tires, in rubber technical industry for production of a wide assortment of rubber technical articles, and in the shoe industry for production of white and colored rubber footwear.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sibur-SKS-30-ARKPN-1st-Group-Styrene-Butadiene-Rubber-SBR.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	27 - 37 @Temperature 100 Â°C	27 - 37 @Temperature 212 Â°F	ML 1-4
Ash	<= 0.80 %	<= 0.80 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	>= 23.0 MPa	>= 3340 psi	
Elongation at Break	>= 560 %	>= 560 %	

Chemical Properties	Metric	English	Comments
Styrene Content	22 - 25 %	22 - 25 %	

Descriptive Properties	Value	Comments
Loss During Drying	<0.4%	
Mass Share Adigol-2	0.7-1.2%	
Mass Share of A-Methyl Styrene	22-25%	
Mass Share of P-23	0.4-1.2%	
Mass Share of VS-30A	1-2%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China