

Sichuan Deyang Haton® 2.2 dtex Polyphenylene Sulfide Staple Fiber

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

Excellent chemical stability Information provided by Sichuan Deyang Chemical Co., LTD

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sichuan-Deyang-Haton-22-dtex-Polyphenylene-Sulfide-Staple-Fiber.php

Physical Properties	Metric	English	Comments
Fiber Count	2.20 dtex	1.98 denier	GB/T14335-2008

Mechanical Properties	Metric	English	Comments
Elongation at Break	54 %	54 %	GB/T1040.2-2006
Tenacity	0.430 N/tex	4.87 g/denier	GB/T14337-2008

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	170 Â°C	338 Â°F	
Oxygen Index	40 %	40 %	GB/T5454-1997

Descriptive Properties	Value	Comments
Length, mm	51,65	
Linear Density, dtex	2.2	GB/T14335-2008

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China