

Sichuan Deyang Haton® 440 dtex Polyphenylene Sulfide Filament

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

Excellent chemical stability Information provided by Sichuan Deyang Chemical Co., LTD

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sichuan-Deyang-Haton-440-dtex-Polyphenylene-Sulfide-Filament.php

| Physical Properties | Metric | English | Comments |
|---------------------|----------|------------|----------------|
| Fiber Count | 440 dtex | 396 denier | GB/T14335-2008 |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|-------------|---------------|-----------------|
| Elongation at Break | 24 % | 24 % | GB/T1040.2-2006 |
| Tenacity | 0.420 N/tex | 4.76 g/denier | GB/T14337-2008 |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|---------|---------|---------------|
| Maximum Service Temperature, Air | 170 Â°C | 338 Â°F | |
| Oxygen Index | 40 % | 40 % | GB/T5454-1997 |

| Descriptive Properties | Value | Comments |
|------------------------|-------------|----------------|
| Linear Density, dtex | 440dex/100f | GB/T14335-2008 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China