

## Sichuan Deyang Haton® hGR40 Polyphenylene Sulfide, Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 40% Glass Fiber Filler

### Material Notes:

Injection molding Information provided by Sichuan Deyang Chemical Co., LTD

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sichuan-Deyang-Haton-hGR40-Polyphenylene-Sulfide-Glass-Fiber-Reinforced.php](http://www.lookpolymers.com/polymer_Sichuan-Deyang-Haton-hGR40-Polyphenylene-Sulfide-Glass-Fiber-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.67 g/cc	0.0603 lb/in <sup>3</sup>	GB/T 1033.1-2008
Water Absorption	0.020 %	0.020 %	GB/T 1034-2008
Linear Mold Shrinkage, Flow	0.0022 cm/cm	0.0022 in/in	GB/T 15585-1995
Linear Mold Shrinkage, Transverse	0.0072 cm/cm	0.0072 in/in	GB/T 15585-1995

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	108	108	GB/T 3398.2-2008
Tensile Strength	180 MPa	26100 psi	GB/T 1040.2-2006
Elongation at Break	1.5 %	1.5 %	GB/T1040.2-2006
Flexural Strength	272 MPa	39500 psi	GB/T 9341-2008
Flexural Modulus	15.2 GPa	2200 ksi	GB/T 9341-2008
Izod Impact, Notched (ISO)	16.0 kJ/m <sup>2</sup>	7.61 ft-lb/in <sup>2</sup>	GB/T 1843-2008
Izod Impact, Unnotched (ISO)	48.0 kJ/m <sup>2</sup>	22.8 ft-lb/in <sup>2</sup>	GB/T 1843-2008

Thermal Properties	Metric	English	Comments
Melting Point	280 °C	536 °F	GBT/T 19466.3-2004
Deflection Temperature at 1.8 MPa (264 psi)	268 °C	514 °F	GB/T 1634.2-2004
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+16 ohm-cm	2.00e+16 ohm-cm	GB/T1410-2006
Surface Resistivity per Square	7.00e+15 ohm	7.00e+15 ohm	GB/T1410-2006
Dielectric Constant	4.0	4.0	GB/T 1409-2006

Dielectric Strength Electrical Properties	16.0 kV/mm Metric	406 kV/in English	GB/T1408.1-2006 Comments
Dissipation Factor	0.0020	0.0020	GB/T 1409-2006

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China