

Sichuan Deyang Haton® hGR515 Polyphenylene Sulfide/PA Alloy

Category : Polymer , Thermoplastic , Nylon , Polyphenylene Sulfide (PPS)

Material Notes:

Injection molding, high strength Information provided by Sichuan Deyang Chemical Co., LTD

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sichuan-Deyang-Haton-hGR515-Polyphenylene-SulfidePA-Alloy.php

Physical Properties	Metric	English	Comments
Density	1.70 g/cc	0.0614 lb/in ³	GB/T 1033.1-2008
Water Absorption	0.020 %	0.020 %	GB/T 1034-2008
Linear Mold Shrinkage, Flow	0.0033 cm/cm	0.0033 in/in	GB/T 15585-1995
Linear Mold Shrinkage, Transverse	0.0033 cm/cm	0.0033 in/in	GB/T 15585-1995

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	110	110	GB/T 3398.2-2008
Tensile Strength	220 MPa	31900 psi	GB/T 1040.2-2006
Elongation at Break	1.4 %	1.4 %	GB/T1040.2-2006
Flexural Strength	330 MPa	47900 psi	GB/T 9341-2008
Flexural Modulus	18.6 GPa	2700 ksi	GB/T 9341-2008
Izod Impact, Notched (ISO)	14.2 kJ/m ²	6.76 ft-lb/in ²	GB/T 1843-2008
Izod Impact, Unnotched (ISO)	66.0 kJ/m ²	31.4 ft-lb/in ²	GB/T 1843-2008

Thermal Properties	Metric	English	Comments
Melting Point	280 °C	536 °F	GBT/T 19466.3-2004
Deflection Temperature at 1.8 MPa (264 psi)	255 °C	491 °F	GB/T 1634.2-2004
Flammability, UL94	V-2	V-2	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.60e+16 ohm-cm	1.60e+16 ohm-cm	GB/T1410-2006
Surface Resistivity per Square	2.00e+15 ohm	2.00e+15 ohm	GB/T1410-2006
Dielectric Constant	4.0	4.0	GB/T 1409-2006

Dielectric Strength Electrical Properties	16.0 kV/mm Metric	406 kV/in English	GB/T1408.1-2006 Comments
Dissipation Factor	0.0020	0.0020	GB/T 1409-2006

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China