

Sika Industry SikaFlex 201 Adhesive

Category : Polymer , Adhesive , Thermoset

Material Notes:

Sika 201 SikaFlex Adhesive Sikaflex 201 meets Federal Specification TT-S-00230C, Type II, Class A and ASTK C-920, Type S, Grade NS. 15 - 15 mm Cut-Off. Good non-sag. Available in black, white, gray, tan, MB bronze. Cure Type: Moisture

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sika-Industry-SikaFlex-201-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0446 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 45	40 - 45	
Tensile Strength, Ultimate	1.38 MPa	200 psi	
Elongation at Break	>= 700 %	>= 700 %	
Adhesive Bond Strength	0.827 MPa	120 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	87.8 Â°C	190 Â°F	
Minimum Service Temperature, Air	-40.0 Â°C	-40.0 Â°F	

Processing Properties	Metric	English	Comments
Cure Time	240 - 480 min	4.00 - 8.00 hour	Tack-free
	1440 min	24.0 hour	Value given per 1/8 inches
Shelf Life	12.0 Month	12.0 Month	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China