

## Silikony Polskie Gumosil B Silicone Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

**Material Notes:**

Flexible with low hardness

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Silikony-Polskie-Gumosil-B-Silicone-Rubber.php](http://www.lookpolymers.com/polymer_Silikony-Polskie-Gumosil-B-Silicone-Rubber.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	Before Curing
Viscosity	20000 cP	20000 cP	Before Curing
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	After Curing

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	After Curing
Tensile Strength at Break	1.50 MPa	218 psi	After Curing
Elongation at Break	150 %	150 %	After Curing

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 Â°C	356 Â°F	

Processing Properties	Metric	English	Comments
Cure Time	<= 1440 min	<= 24.0 hour	Curing
Pot Life	30 min	30 min	Curing

Descriptive Properties	Value	Comments
Color	White	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China