

Silikony Polskie Gumosil WW Silicone Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

Flexible with good tearing resistance

Order this product through the following link:

http://www.lookpolymers.com/polymer_Silikony-Polskie-Gumosil-WW-Silicone-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	Before Curing
Viscosity	30000 cP	30000 cP	Before Curing
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	After Curing

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	After Curing
Tensile Strength at Break	4.00 MPa	580 psi	After Curing
Elongation at Break	400 %	400 %	After Curing

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 Å°C	356 Å°F	

Processing Properties	Metric	English	Comments
Cure Time	<= 1440 min	<= 24.0 hour	Curing
Pot Life	30 min	30 min	Curing

Descriptive Properties	Value	Comments
Color	Beige	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China