

Silikony Polskie Polastosil M-99 Silicone Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

Rubber with strong hardness

Order this product through the following link:

http://www.lookpolymers.com/polymer_Silikony-Polskie-Polastosil-M-99-Silicone-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	Before Curing
Viscosity	900 cP	900 cP	Before Curing
Linear Mold Shrinkage	0.025 cm/cm	0.025 in/in	After Curing

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	After Curing
Tensile Strength at Break	2.00 MPa	290 psi	After Curing
Elongation at Break	100 %	100 %	After Curing

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 Â°C	356 Â°F	

Processing Properties	Metric	English	Comments
Cure Time	<= 1440 min	<= 24.0 hour	Curing
Pot Life	10 min	10 min	Curing

Descriptive Properties	Value	Comments
Color	White	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China