

Solvay Engineered Polymers DEXFLEX® 930 TPO (discontinued **)

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Olefinic Elastomer (TPO) , Polyolefin

Material Notes:

Description: DEXFLEX® 930 is a thermoplastic olefinic elastomer (TPO) designed for large automotive exterior applications that require high flow for excellent processability, ductile impact properties at low temperatures, and good paint adhesion. Applications: Bumper fascias and exterior trim Information provided by Solvay Engineered Polymers. LyondellBasell acquired Solvay Engineered Polymers in 2008. This grade is not part of the current LyondellBasell product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Engineered-Polymers-DEXFLEX-930-TPO-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 g/cc	0.950 g/cc	ISO 1183
Linear Mold Shrinkage	0.0070 - 0.010 cm/cm	0.0070 - 0.010 in/in	as molded; ISO 294
	0.0090 - 0.012 cm/cm	0.0090 - 0.012 in/in	after bake; ISO 294
Melt Flow	21 g/10 min	21 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	15.0 MPa	2180 psi	150x10x4 mm specimen, 50 mm/min; ISO 527-1/527-2
Flexural Modulus	0.940 GPa	136 ksi	80x10x4 mm specimen, 2 mm/min; ISO 178
Impact Test	18.0 J	13.3 ft-lb	multiaxial, 2.2 m/s; ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear	55.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	30.6 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM E228
	@Temperature -30.0 - 80.0 °C	@Temperature -22.0 - 176 °F	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China